

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**


THIS PAGE BLANK (USPTO)



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : A61M 29/00	A1	(11) International Publication Number: WO 95/09667 (43) International Publication Date: 13 April 1995 (13.04.95)
(21) International Application Number: PCT/US94/10961 (22) International Filing Date: 28 September 1994 (28.09.94) (30) Priority Data: 08/130,283 1 October 1993 (01.10.93) US (71) Applicant: BOSTON SCIENTIFIC CORPORATION [US/US]; 480 Pleasant Street, Watertown, MA 02172-2407 (US). (72) Inventors: HAMILTON, Bruce; 22 Veritas Avenue, Lowell, MA 01854 (US). SAHATJIAN, Ronald, A.; 29 Saddle Club Road, Lexington, MA 02173 (US). (74) Agents: CRAIG, Frances, P. et al.; 24 North Street, Salem, MA 01970 (US).		(81) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>

(54) Title: MEDICAL DEVICE BALLOONS CONTAINING THERMOPLASTIC ELASTOMERS



(57) Abstract

A dilatation balloon and catheter for insertion into a bodily conduit. The catheter (10) includes shaft (12) and a dilatation balloon (24) at the distal end of the shaft. The balloon is inflated via a central lumen (14) in the shaft for delivery of a fluid inflation media. The balloon is fabricated from a combination of a thermoplastic elastomer (TPE), preferably an engineering thermoplastic elastomer (ETE), with a non-compliant structural polymeric material. The combination may be a blend of the non-compliant structural polymer and the TPE. Alternatively, the combination may be a layered balloon having, for example, a non-compliant structural polymer inner layer and a soft, abrasion resistant, elastomeric outer layer. Methods for fabricating the balloon from the combination of a TPE and a non-compliant structural polymer are also disclosed.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

MEDICAL DEVICE BALLOONS CONTAINING
THERMOPLASTIC ELASTOMERS

BACKGROUND OF THE INVENTION

5 The present invention relates to catheters that can be placed in bodily conduits. The invention particularly relates to dilatation balloons and catheters using such balloons for administering treatments to widen constricted passages in, for example, angioplasty, valvuloplasty, or
10 urological procedures.

 One example of such a procedure, angioplasty, is used to treat a stenosis, i.e. to restore adequate blood flow to a region of a blood vessel which has been narrowed to such a degree that blood flow is restricted. Frequently the
15 stenosis can be expanded so that the vessel will permit an acceptable blood flow rate. Coronary angioplasty, for example, includes the insertion of a balloon catheter through a patient's coronary artery to an arterial stenosis and injecting a suitable fluid into the balloon to inflate
20 it, hence expanding the stenosis radially outwardly. Angioplasty has proven to be a successful alternative to coronary arterial bypass surgery.

 Typically, balloon catheters have a balloon fastened at at least one end around the exterior of a hollow catheter
25 shaft. The hollow interior of the balloon is in fluid flow relation with the hollow interior of the shaft. The shaft then may be used to provide a fluid supply for inflating the balloon.

 Presently used catheter balloons may be classified as
30 compliant or non-compliant balloons. Compliant balloons expand and stretch with increasing pressure within the balloon, and are made from such materials as polyethylene or polyolefin copolymers. Non-compliant balloons, made from such materials as polyethylene terephthalate (PET) or
35 polyamides, remain at a preselected diameter as the internal

balloon pressure increases beyond that required to fully inflate the balloon.

Compliant balloon materials provide a degree of softness to the balloon which aids its passage through, e.g., blood vessels with minimal trauma. Known compliant balloon materials also can display good abrasion and puncture resistance at thicknesses typically used for medical device balloons. However, as mentioned above, they do not remain at the desired diameter with increasing pressure. Such compliant balloons also lack sufficient hoop strength to achieve high dilating forces.

A non-compliant balloon, that is one remaining at a preselected diameter regardless of increasing pressure, is often desirable. Typical non-compliant balloon materials do not exhibit the same degrees of softness and abrasion resistance as the compliant balloons.

It would be desirable, for many treatment conditions, to have a dilatation balloon exhibiting the combined characteristics of softness, abrasion and puncture resistance, hoop strength, and the ability to maintain a preselected diameter as the internal pressure within the balloon is increased. The balloon described herein was developed to address that need.

SUMMARY OF THE INVENTION

In one embodiment, the invention is a dilatation balloon for use in a medical catheter device. The dilatation balloon includes a thermoplastic elastomer in combination with a non-compliant structural polymeric material. The preferred thermoplastic elastomer includes an engineering thermoplastic elastomer, for example a polyether glycol/polybutylene terephthalate block copolymer. The thermoplastic elastomer may be combined with the non-compliant structural polymeric material as an outer elastomeric layer disposed upon an inner structural layer of the non-compliant structural polymeric material, as both an

inner elastomeric layer and an outer elastomeric layer disposed upon an intermediate structural layer of the non-compliant structural polymeric material, or as a blend of the thermoplastic elastomer and the non-compliant structural polymeric material.

5 In another embodiment, the invention is a catheter for insertion into a bodily conduit. The catheter includes a shaft having a lumen internal to the shaft for delivery of fluid inflation media, and a dilatation balloon bonded to the shaft and defining a chamber. The chamber is in fluid communication with the lumen to permit inflation of the chamber. The dilatation balloon includes a thermoplastic elastomer in combination with a non-compliant structural polymeric material, as described above with respect to the balloon in accordance with the invention.

10 In yet another embodiment, the invention is a method for fabricating a dilatation balloon for use in a medical catheter device. The method involves producing a generally cylindrical balloon blank from a combination of a thermoplastic elastomer and a non-compliant structural material, and shaping the balloon blank to produce the dilatation balloon.

15 The balloon blank may be produced by disposing an elastomeric layer including the thermoplastic elastomer upon a structural layer including the non-compliant structural polymeric material to produce a layered, generally cylindrical balloon blank. The thermoplastic elastomer and the non-compliant structural polymeric material may be coextruded to produce the balloon blank. Alternatively, the balloon blank may be produced by preparing a blend of the thermoplastic elastomer and the non-compliant structural polymeric material. A generally cylindrical balloon blank is formed from the blend, and the balloon blank is then shaped to produce the dilatation balloon. The balloon blank may be shaped to have a generally cylindrical central portion and generally conical end portions.

BRIEF DESCRIPTION OF THE DRAWINGS

For a better understanding of the present invention, together with other objects, advantages, and capabilities thereof, reference is made to the following Description and appended Claims, together with the Drawings in which:

Figure 1 is an elevation view of a medical balloon catheter, partly in section, in accordance with one embodiment of the present invention;

Figure 2a is a cross-sectional view of the balloon of Figure 1, taken along line 2a-2a, showing the balloon layers;

Figures 2b, 2c, and 2d are cross-sectional views similar to that shown in Figure 2a (omitting the shaft distal end) illustrating balloons in accordance with alternate embodiments of the invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

An exemplary embodiment of the balloon and catheter in accordance with the invention is described herein. The angioplasty catheter includes a balloon mounted at the distal end of a shaft including at least one lumen for inflation of the balloon. The balloon is a generally tubular body fabricated from a combination of a non-compliant structural polymeric material and a thermoplastic elastomer (TPE). The combination may be in the form of coextensive coextruded layers, otherwise disposed layers, blends, or blended layers of these materials. Once the catheter is in position within the patient's artery, a fluid inflation medium may be introduced via the lumen to inflate the balloon to the preselected desired diameter.

The term "structural polymer" or "structural polymeric material", as used herein, is intended to mean any polymeric material suitable for use in medical balloons and compatible with the TPE selected. As mentioned above, the term "non-compliant", as used herein, is intended to mean remaining at a preselected diameter as the internal pressure in the

balloon is increased above that required to fully inflate the balloon. The structural layer of the balloon must be self supporting and capable of supporting at least one TPE layer thereon. Suitable non-compliant structural polymeric materials include, for example, modified polyesters, polyethylene terephthalate (PET), modified polybutylenes, polyvinyl chlorides, polyamides (e.g. Nylon), etc., or a combination thereof. Preferred are biaxially oriented non-compliant structural materials; most preferred is biaxially oriented PET.

The term "thermoplastic elastomer" or "TPE", as used herein, is intended to mean a polymeric material that combines the mechanical properties of a thermoset rubber, i.e. resiliency, softness, and toughness, with the production economics of a thermoplastic polymer. The TPEs include styrenic block copolymers, polyolefin blends (TPOs), elastomeric alloys, thermoplastic polyurethanes (TPUs), thermoplastic copolyesters, and thermoplastic polyamides. These materials have varying patterns of hard and soft segments included in the polymer chain or compound. The hard segments melt or soften at processing temperatures, producing a melt processable material for ease of fabrication. In block copolymer TPEs, the hard and soft regions are in the same polymer chain. Descriptions of various types of TPEs may be found in Modern Plastics Encyclopedia 1988, Vol. 64, No. 10A, pp. 93 - 100 (October 1987), and in Modern Plastics Encyclopedia 1990, Vol. 66, No. 11, pp. 122 - 131 (Mid-October 1989), both incorporated herein by reference.

The preferred TPEs for the balloon described herein are engineering thermoplastic elastomers (ETEs), which are randomized block copolymers having polyester crystalline hard segments and amorphous glycol soft segments. ETEs possess flexibility over a useful range of strain, and are quite extensible when operating within their elastic limit. Another advantage of ETEs for medical devices is their

resistance to most radiation, permitting sterilization by such means, although they must be protected from UV radiation.

5 The more preferred ETes for use in the medical devices described herein are randomized block copolymers of polyether glycol and polybutylene terephthalate (PBT). These combine crystalline PBT hard segments with melt stable glycol soft segments, and come in a wide range of stiffness grades. Most preferred are those having a flexural modulus
10 of about 21,000 - 440,000 psi (as measured in accordance with ASTM D790, Method 1), for example Hytrel® polymers (available from E.I. DuPont de Nemours and Company, Wilmington, DE).

As mentioned above, the combination of a TPE and a non-compliant structural polymer may be in the form of blends,
15 coextensive coextruded layers, otherwise disposed layers, or layers of blends of these materials. Suitable blends include homogeneous and near-homogeneous blends, which may be prepared by such conventional means as stirring, mixing,
20 compounding, etc.

In a layered embodiment of the balloon, one or more base structural polymer layers are formed, for example by extrusion, from a non-compliant structural polymer, as described above. Alternatively, the base non-compliant
25 structural layer is formed from a blend of two or more structural polymers, a blend of a structural polymer with a minor amount of another polymeric material, or a blend of a structural polymer with a minor amount of a TPE. As used herein, the term "minor amount" is intended to mean an
30 amount selected to make the additive no more than a secondary component, for example less than 50 weight %, of the blend. The material of the structural layer, however, must still contribute to the balloon the properties described above for the structural material. This base
35 structural layer (or layers) is typically at least about

0.2 - 1.5 mil thick, and gives the balloon its tensile strength so that the balloon wall is self supporting.

At least one additional, elastomeric outer layer about 0.2 - 0.5 mil thick is coextruded with or otherwise disposed on the base layer and, typically, generally coextensive therewith. Normally, the elastomeric layer is significantly thinner than the structural layer. The material of this outer layer is based on a thermoplastic elastomer (TPE) which, in some embodiments, may be combined in a blend with other polymers known to be suitable for medical balloons. The amount of these other polymers, however, should be within limits which would permit such a blend to contribute to the balloon the properties described herein for such an elastomeric layer. Especially preferred for this outer elastomeric layer is a blend of an ETE with a small amount of a non-compliant structural polymer, e.g. a blend of about 1 - 10 weight % PET, remainder Hytrel elastomer.

In some of the above-described layered balloons, it may be advantageous to dispose or coextrude an adhesive or other polymer layer between two or more of the layers. In one embodiment, an adhesive layer may be included to improve adhesion between coextensive balloon layers and, if desired, may be applied for adhesion of the medical device balloon to a catheter shaft. In another embodiment, an additional polymer layer may be included to contribute other desirable properties to the balloon, for example to contribute further to the softness and/or foldability of the balloon. In other embodiments, the adhesive or other polymer may be blended with a structural and/or elastomeric layer to contribute its properties to the balloon. For example, in a three layer balloon an adhesive polymer may be blended with a structural polymer layer to improve adhesion of inner and outer ETE layers to the structural layer. The amount of adhesive or other polymer in such a blend is selected to provide the desired enhancement of properties while permitting the blend to possess the properties described herein for such a layer.

Examples of adhesive materials for forming this layer or blend are Bynel® adhesive resin (E.I. DuPont de Nemours and Company, Wilmington, DE) or Plexar® adhesive resin (Quantum Chemical Corp., Cincinnati, OH). Selar® modified PET resin (E.I. DuPont de Nemours and Company, Wilmington, DE) is a suitable polymer intermediate layer or blend additive for improving softness and foldability of the balloon. Bynel and Plexar resins can also serve to improve the abrasion resistance and puncture resistance of the balloon, and provide it with a softer feel.

In another embodiment of the balloon, a single layer balloon wall is fabricated from a blend of a non-compliant structural polymer and a TPE. The TPE, preferably the above-described polyether glycol/PBT block copolymer, is blended with the structural polymer in a TPE-to-structural polymer ratio selected to provide the desired degree of softness and abrasion resistance to the balloon without unduly compromising the hoop strength or the desired inflated diameter. As mentioned above, such blends may be homogeneous or near-homogeneous, and may be blended in any of several ways known in the art. Typical polymer ratios for such a single layer balloon are about 40:60 to 60:40, TPE:structural polymer.

In other embodiments, the TPE/structural polymer blend used in the above-described single layer balloon may be used as a structural layer in combination with other layers, or may be blended to be used as an elastomeric layer in a layered balloon. The polymer ratio for a blended structural layer of such a balloon is typically about 40:60 to 60:40, TPE:structural polymer; that for elastomeric inner or outer layers is typically about 30:70 to 60:40, TPE:structural polymer. The exact ratios within these ranges to produce specific balloon characteristics are empirically determined with minimal experimentation. These blended layers may be used with or without an adhesive or softening component or layer as described above

The use of thermoplastic elastomers in medical device balloons results in a superior balance of balloon properties when used as one or more outer layers over a structural layer of currently used balloon materials or other suitable structural polymers, or as outer and inner layers surrounding such a structural layer. Alternatively, this superior balance of balloon properties may be achieved by using TPEs as a blend with currently used balloon materials or other suitable structural polymers. By varying the fabrication method and/or layer materials and/or blend materials and ratios, as described herein, the structural and surface properties of the ETE containing balloon may be precisely tailored for a desired procedure.

The description below of various illustrative embodiments shown in the Drawings refers to engineering thermoplastic elastomers (ETEs). However, it is not intended to limit the scope of the present invention, but merely to be illustrative and representative thereof.

Referring now to Figure 1, catheter 10 in accordance with one embodiment of the present invention includes shaft 12 having lumens 14 and 16 extending therethrough, and having a proximal end 18 and a distal end 20. Distal end 20 extends to catheter tip 22. Dilatation balloon 24, shown in Figure 1 in its inflated state, surrounds shaft distal end 20. Balloon proximal end 26 is bonded to shaft distal end 20 at a point spaced from tip 22, and balloon distal end 28 is bonded to shaft distal end 20 near tip 22, each, e.g., by a suitable adhesive (not shown). Balloon 24 defines balloon chamber 30 which is in fluid communication with lumen 14 via aperture 32. Thus, balloon 24 may be inflated by passing a fluid inflation medium through lumen 14 and aperture 32 into chamber 30. Lumen 16 may be used, for example, to contain a guidewire or other device.

As shown in Figures 1 and 2a, dilatation balloon 24 surrounding shaft distal end 20 is made up of two layers, 34 and 36, of differing polymeric materials. Inner layer 34 is

a structural layer of, e.g., PET approximately 0.2-1.0 mil thick. Outer layer 36 has been co-extruded to be co-extensive with layer 34, and is a layer of ETE, e.g. Hytrel copolymer, about 0.2 - 0.5 mil thick.

5 Figures 2b, 2c, and 2d each illustrate alternate embodiments of the balloon of the invention in cross-section, similarly to Figure 2a. For simplicity, however, shaft distal end 20, although actually present in the same position as shown in Figure 2a, is not depicted in the view
10 shown in Figures 2b-2d.

Figure 2b illustrates in cross-section dilatation balloon 24a, fabricated from single layer 38 of a blend of a structural polymer, e.g. polyethylene terephthalate, with an ETE, for example Hytrel copolymer.

15 Figure 2c shows balloon 24b fabricated from, e.g., coextruded triple layers, 34a, 36a, and 40. Structural layer 34a and ETE outer layer 36a are similar to layers 34 and 36 of Figures 1 and 2a. In the embodiment illustrated in Figure 2c, however, an additional ETE layer, innermost
20 layer 40, has been coextruded to be coextensive with layers 34a and 36a and internal thereto. Innermost layer 40 provides additional tear resistance to protect the balloon wall from damage from internal pressure. Layer 40 also provides for a softer, more foldable balloon.

25 Figure 2d illustrates balloon 24c, fabricated in a similar manner to balloon 24 of Figures 1 and 2a, and having inner structural layer 34b and ETE outer layer 36b. Thin intermediate adhesive layer 42 of, e.g., Bynel resin is coextruded with and between layers 34b and 36b to be
30 coextensive therewith, acting to bond together more securely layers 34b and 36b.

 In other alternate embodiments, one or more of layers 34, 34a, and 34b may be a blend of a structural polymer with an ETE. Also alternatively, one or more of layers 36, 36a,
35 36b, or 40 may be a blend of ETE with a structural polymeric material. In the embodiment of Figure 2c, a sufficient

amount of a polymeric adhesive to improve bonding of the layers may be blended into layer 34a. Alternatively, layer 34a may be , e.g., a Selar resin balloon softening layer. Also alternatively, the adhesive or other polymeric additive may be blended into, e.g., layer 34, 36, 36a, 40, etc., as described above. In other alternate embodiments, not shown, the balloon may have more than one innermost and/or outermost ETE layer. For example, a balloon may be similar to that shown in Figure 2a but have an additional ETE layer between layers 34 and 36, or may be similar to that shown in Figure 2c but have an additional ETE layer between layers 34a and one or both of layers 36a and 40.

In operation, the catheter device including the novel dilatation balloon is inserted into the vasculature of a patient, and is manipulated into position by torquing, pushing, and pulling. Positioning of the catheter is aided by the softness of the balloon provided by the TPE component of the balloon. Once the catheter is in position, the balloon is inflated to the preselected diameter, then deflated via the central lumen of the shaft. The inclusion of a non-compliant structural polymer in the balloon makes possible such preselection of the diameter. Upon completion of the dilation procedure and deflation of the balloon, the catheter is removed from the patient. Removal of the catheter is also aided by the softness contributed to the balloon by the TPE component.

The invention described herein presents to the art novel, improved catheters and composite medical device balloons including thermoplastic elastomers as (a) one or more layers in addition to one or more layers of currently used balloon structural materials or other suitable structural polymers, or (b) as a blend with such materials. The inclusion of TPE results in a superior balance of balloon properties. For example, softer feel; superior abrasion and puncture resistance; lower required insertion, placement, and withdrawal forces; lower balloon resistance

to inflation and deflation pressure; superior refoldability, with fold memory; and the ability to maintain a preselected diameter are all achievable in a single balloon fabricated as described herein. Thus, the balloon described herein can provide a non-compliant balloon with the softness of a compliant balloon, as well as a soft balloon with ranges of burst strength and hoop strength equivalent to those of harder balloons. The use of the adhesives and other layers or layer additives described herein, especially the Bynel and Plexar adhesives and Selar additive described, can offer advantageous adhesive and/or softening properties. By varying the fabrication method and/or layer or blend materials and ratios as described herein, the balance of structural and surface properties of the TPE containing balloon may be precisely tailored for a specific procedure.

While there has been shown and described what are at present considered the preferred embodiments of the invention, it will be apparent to those skilled in the art that modifications and changes can be made therein without departing from the scope of the present invention as defined by the appended Claims.

WE CLAIM:

1. A dilatation balloon for use in a medical catheter device, said dilatation balloon comprising a thermoplastic elastomer in combination with a non-compliant structural polymeric material.

2. A balloon in accordance with claim 1 wherein said thermoplastic elastomer comprises an engineering thermoplastic elastomer.

3. A balloon in accordance with claim 2 wherein said engineering thermoplastic elastomer is a polyether glycol/polybutylene terephthalate block copolymer.

4. A balloon in accordance with claim 1 wherein said thermoplastic elastomer is combined with said non-compliant structural polymeric material as an outer elastomeric layer disposed upon an inner structural layer of said non-compliant structural polymeric material.

5. A balloon in accordance with claim 1 wherein said thermoplastic elastomer is combined with said non-compliant structural polymeric material as both an inner elastomeric layer and an outer elastomeric layer disposed upon an intermediate structural layer of said non-compliant structural polymeric material.

6. A balloon in accordance with claim 1 wherein said thermoplastic elastomer is combined with said non-compliant structural polymeric material as a blend of said thermoplastic elastomer and said non-compliant structural polymeric material.

7. A balloon in accordance with claim 6 wherein said blend comprises a structural layer and said balloon further comprises an elastomeric layer disposed upon said structural layer, said elastomeric layer comprising a thermoplastic elastomer.

5

8. A balloon in accordance with claim 7 wherein said blend comprises a ratio of about 40:60 to about 60:40, thermoplastic elastomer to non-compliant structural polymeric material.

9. A balloon in accordance with claim 6 wherein said blend comprises an elastomeric layer and said balloon further comprises a structural layer upon which said elastomeric layer is disposed.

10. A balloon in accordance with claim 9 wherein said blend comprises a ratio of about 30:70 to about 60:40, thermoplastic elastomer to non-compliant structural polymeric material.

11. A catheter for insertion into a bodily conduit, said catheter comprising:

a shaft including a lumen internal to said shaft for delivery of fluid inflation media; and

5

a dilatation balloon bonded to said shaft and defining a chamber, said chamber being in fluid communication with said lumen to permit inflation of said chamber, wherein said dilatation balloon comprises a thermoplastic elastomer in combination with a non-compliant structural polymeric material.

10

12. A catheter in accordance with claim 11 wherein said thermoplastic elastomer is an engineering thermoplastic elastomer.

13. A catheter in accordance with claim 11 wherein said thermoplastic elastomer is combined with said non-compliant structural polymeric material as an outer elastomeric layer disposed upon an inner structural layer of said non-compliant structural polymeric material.

14. A catheter in accordance with claim 11 wherein said thermoplastic elastomer is combined with said non-compliant structural polymeric material as both an inner elastomeric layer and an outer elastomeric layer disposed upon an intermediate structural layer of said non-compliant structural polymeric material.

15. A catheter in accordance with claim 11 wherein said thermoplastic elastomer is combined with said non-compliant structural polymeric material as a blend of said thermoplastic elastomer and said non-compliant structural polymeric material.

16. A method for fabricating a dilatation balloon for use in a medical catheter device, said method comprising the steps of:

producing a generally cylindrical balloon blank from a combination of a thermoplastic elastomer and a non-compliant structural material; and

shaping said balloon blank to produce said dilatation balloon.

17. A method in accordance with claim 16 wherein said balloon blank producing step comprises disposing an elastomeric layer comprising said thermoplastic elastomer upon a structural layer comprising said non-compliant structural polymeric material to produce a layered, generally cylindrical balloon blank.

18. A method in accordance with claim 17 wherein said disposing step comprises coextruding said thermoplastic elastomer and said non-compliant structural polymeric material.

19. A method in accordance with claim 17 wherein said disposing step comprises disposing said structural layer as an inner layer and disposing said thermoplastic elastomer as an outer elastomeric layer on said inner structural layer.

20. A method in accordance with claim 17 wherein said disposing step comprises disposing said structural layer as an intermediate layer and disposing said thermoplastic elastomer as both an outer and an inner elastomeric layer on said intermediate structural layer.

21. A method in accordance with claim 16 wherein said balloon blank producing step comprises: preparing a blend of a thermoplastic elastomer and a non-compliant structural polymeric material; and forming a generally cylindrical balloon blank from said blend.

22. A method in accordance with claim 16 wherein said shaping step comprises shaping said balloon blank such that said dilatation balloon has a generally cylindrical central portion and generally conical end portions.

FIG. 1





FIG. 2a




FIG. 2b




FIG. 2c




FIG. 2d

A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) :A61M 29/00

US CL :604/96

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 428/35.02; 604/96-103; 606/192-195

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
NONEElectronic data base consulted during the international search (name of data base and, where practicable, search terms used)
NONE**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X --- Y	US, A, 5,192,296, (BHATE ET AL.), 09 March 1993. See column 6, lines 38-68.	1, 4, 5, 11, 13, 14, 16-22 ----- 2, 3, 6-10, 12, 15
Y	US, A, 5,195,969, (WANG ET AL.), 23 March 1993. See column 3, lines 2 and 3.	6-10, 15
A, P	US, A, 5,270,086, (HAMLIN), 14 December 1993.	1, 16
A	US, A, 5,207,700, (EUTENEUER), 04 May 1993.	16

☒ Further documents are listed in the continuation of Box C.
 ☐ See patent family annex.

* Special categories of cited documents:	*T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
A document defining the general state of the art which is not considered to be part of particular relevance	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
E earlier document published on or after the international filing date	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Z*	document member of the same patent family
O document referring to an oral disclosure, use, exhibition or other means		
P document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

10 NOVEMBER 1994

Date of mailing of the international search report

15 DEC 1994

 Name and mailing address of the ISA/US
 Commissioner of Patents and Trademarks
 Box PCT
 Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

FRANK WILKENS, III

Telephone No. (703) 308-2681

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A, P	US, A, 5,290,306 (Trotta et al.) 01 March 1994	1

THIS PAGE BLANK (USPTO)